MUCOPREN® SOFT – RELIABLE HOLD. NOTICEABLE COMFORT.

A-SILICONE FOR LONG-LASTING SOFT RELINING

Special long-term adhesion:
Excellent adhesion to acrylic dentures through patented **MUCOPREN®** ADHESIVE
» Only a single application necessary!

Unique sealing through its very smooth, hydrophobic silicone surface: Inhibits bacterial colonization thus ensuring hygienic conditions on the prosthesis[1)]



www.kettenbach-dental.us
Strong in prevention – restoration – impressions.

[1)] Result from in-vitro studies in which it was shown that the growth of Candida albicans was prevented thanks to the smooth silicone surface.

KETTENBACHDENTAL
Simply intelligent

DELIVERS WHAT IT PROMISES

SIMPLE TREATMENT & FAST PROCESSING

Short setting and waiting times ensure a fast, smooth workflow in the dental office and laboratory.

Application video

3 MIN.

Chairside (direct application): 3 min. waiting time after removal from the mouth

Labside (indirect application): 3 min. waiting time in the pressure pot/water bath



HIGH WEARING COMFORT

Odor and taste neutrality make wearing the denture comfortable.

DIVERSE RANGE OF INDICATIONS

- For pressure equalization in mucosal areas with varying degrees of resilience and to relieve sharp bony edges.
- For relieving pressure on the surgical site after implant placement and promoting osseo-integration
- For relining interim dentures and for use as a mucosal conditioner in case of denture stomatitis



RANGE

MUCOPREN® SOFT Basic set	REF 28105	50 ml MUCOPREN® SOFT, 50 ml silicone sealant, 10 ml MUCOPREN® ADHESIVE and accessories
MUCOPREN® SOFT Normal pack	REF 15687	2 x 50 ml MUCOPREN® SOFT, 6 white mixing tips
MUCOPREN® SILICONE SEALANT	REF 15686	50 ml MUCOPREN® SILICONE SEALANT, 8 orange mixing tips
MUCOPREN® ADHESIVE	REF 14203	10 ml MUCOPREN® ADHESIVE

TECHNICAL DATA

Product name	Mixing ratio	Working time at 23°C ≤	Intraoral setting time at 35°C ≥	Water bath	End of setting ≥	Shore hardness (approx.)
MUCOPREN® SOFT – direct relining	1:1	2:15 min.	3:15 min.	Not applicable	5:30 min.[2)]	A 28
MUCOPREN® SOFT – indirect relining	1:1	2:15 min.	Not applicable	3:00 min.	> 3 min.	A 28
MUCOPREN® SILICONE SEALANT	1:1	1:30 min.	Not applicable	Not applicable	6:30 min. at 23°C	A 33

[2)] Total setting time (removal time from mouth) from the start of mixing

MORE INFORMATION

Kettenbach LP
16052 Beach Blvd. Ste. 221 · Huntington Beach, CA 92647, USA
877-532-2123 · Custservice@kettenbachusa.com
Website: www.kettenbach-dental.us · Web shop: www.kettenbachusa.com
Strong in prevention – restoration – impressions.

0211354_4526

KETTENBACH DENTAL
Simply intelligent